

# INDION® 222 Na

# **Description**

INDION 222 Na is a high capacity strongly acidic cation exchanger in bead form. It is based on cross linked polystyrene and has a gel structure. The resin contains sulphonic acid functional groups. It is supplied moist in the sodium form.

# **Applications**

INDION 222 Na is used most widely in sodium form for water softening application. It can be used also in two-stage de-ionising as the cation exchanger in the hydrogen cycle.

## **Characteristics**

Appearance : Golden yellow beads

Matrix : Styrene divinylbenzene copolymer

Functional Group : Sulphonic acid

Ionic form as supplied : Sodium

Total exchange capacity : 1.92 meg/ml, minimum

Moisture holding capacity : 47 - 53 %

Shipping weight \* : 820 kg/m³, approximately

Particle size range : 0.3 to 1.2 mm

> 1.2 mm : 5.0%, maximum < 0.3 mm : 1.0%, maximum Uniformity co-efficient : 1.7, maximum

Effective size : 0.45 to 0.55 mm

Operating pH range : 0 to 14

Maximum operating temperature : 140° C

Resistance to reducing agents : Good

Resistance to oxidizing agents : Generally good, chlorine should be absent

<sup>\*</sup> Weight of resin, as supplied, occupying 1 m<sup>3</sup> in a unit after backwashing and draining.

## **Packing**

HDPE Lined bags 25/50 lts LDPE bags 1 cft/25 lts Super sack 1000 lts Super sack 35 cft MS drums Fiber drums 180 lts with liner bags with liner bags 7 cft

## Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry. Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20° C and 40° C.

## Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

**INDION** is the registered trademark of Ion Exchange (India) Ltd.



#### CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011 Tel: 022-3989 0909 Fax: 022-2493 8737

E-mail: ieil@ionexchanae.co.in

#### INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701 Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918

E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

### **REGIONAL OFFICES**

• Chennai - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361 E-mail: checro@ionexchange.co.in

- Tel: 011-3989 0909/3054 3200 Delhi Fax: 011-2577 4837 E-mail: delcro@ionexchange.co.in

- Tel: 033-3989 0909/3043 3400 Kolkata Fax: 033-2400 4345 E-mail: calcro@ionexchange.co.in

• Vashi - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839 E-mail: mumcro@ionexchange.co.in

#### **BRANCH OFFICES**

Tel: 080-2204 2888 • Bengaluru

E-mail: bngcro@ionexchange.co.in

- Tel: 0674-326 9525 • Bhubaneswar

E-mail: bbsr@ionexchange.co.in

- Tel: 0172-274 5011 • Chandigarh Fax: 0172-274 4594

E-mail: delcro@ionexchange.co.in

• Hyderabad - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104 E-mail: hydcro@ionexchange.co.in

• Lucknow - Tel: 0522-301 3401/02 Fax: 0522- 301 3401

E-mail: luk.general@ionexchange.co.in

- Tel: 0265-302 7489/90 Fax: 0265-239 8508 Vadodara

E-mail: brdcro@ionexchange.co.in

- Tel: 0891-324 6253 Visakhapatnam

E-mail: sales.vizag@ionexchange.co.in

FACTORIES: Ankleshwar · Hosur · Patancheru · Rabale · Verna ALL INDIA SERVICE AND DEALER NETWORK

Visit us at: www.ionindia.com